

# MATERIAL- DATA SHEET

RHEINZINK-GRANUM  
skygrey



- LIGHT-PHOSPHATED SURFACE
- NOBLE, MATT LOOK WITH ZINC TYPICAL STRUCTURE
- DURABLE AND WEATHER RESISTANT
- EXCELLENT PROCESSABILITY

## BASIC-INFORMATION

---

The RHEINZINK-GRANUM product line stands for a noble, matt appearance. Characteristic for GRANUM is its durable phosphate coating, which gives an idea of the zinc-typical structure of the natural patina. GRANUM-skygrey is the light-phosphated surface variation, which presents itself aesthetically and authentically in its self. The environmentally friendly material offers weather resistant protection for a consistent appearance.

Specific weight 7.2 g/cm<sup>3</sup>

Building material class A1 (non-combustible)

Titanium zinc according to DIN EN 988

## DELIVERY FORM

---

Standard widths	500 – 600 – 650 – 670 – 1000 mm
Standard thicknesses	0.65 – 0.70 – 0.80 – 1.00 mm
Protective film	Standard
Coil inner diameter	508 mm at > 500 kg 400 mm at < 500 kg

## IMPORTANT INSTALLATION INSTRUCTIONS

---

Bending radius	Minimum 1.75 mm, from 1.00 mm on 1.75 x t
Soldering recommendation	Soldering flux "ZD-pro" (company Felder), remove the coating abrasively, overlap area 10 to 15 mm
Processing temperature	Warming up in temperatures below 10°
Protective film	Remove the film immediately after assembly

RHEINZINK GmbH & Co. KG  
Bahnhofstraße 90  
45711 Datteln · Germany  
Tel.: +49 2363 605-490  
Fax: +49 2363 605-291  
E-Mail: info@rheinzink.com

[www.rheinzink.com](http://www.rheinzink.com)

*Note:*

*In the event of contamination due to external or environmental influences, please request the RHEINZINK cleaning recommendations. With these recommendations, RHEINZINK cannot guarantee that a new look will be created.*

# MATERIAL- DATA SHEET

RHEINZINK-GRANUM  
skygrey



## ALLOY

Zinc	99.995% (Z1 according DIN EN 1179)
Copper	0.10 – 0.20%
Titanium	0.07 – 0.12%
Aluminum	≤ 0.015%

## CERTIFICATION

Quality management	Certified according to EN 988
--------------------	-------------------------------

## MECHANICAL-TECHNOLOGICAL PROPERTIES

0.2% proof stress (Rp0.2)	≥ 110 N/ mm <sup>2</sup>
Tensile strength (Rm)	≥ 150 N/ mm <sup>2</sup>
Breaking elongation (A50)	≥ 40%
Vickers hardness (HV3)	≥ 45
Folding test	no cracks on the bending edge
Bending back after folding test	no cracks after bend break
Erichsen cupping	≥ 8,0 mm
Permanent elongation in creep (Rp0.1)	≤ 0,1%

## PHYSICAL AND CHEMICAL PROPERTIES

Melting point / range	420 °C
Boiling point / range	906 °C
Recrystallization limit	> 300 °C
Density at 20 °C	7.2 g/ cm <sup>3</sup>
Expansion coefficient	
In the longitudinal direction	22·10 <sup>-6</sup> K <sup>-1</sup>
In the rolling transverse direction	17·10 <sup>-6</sup> K <sup>-1</sup>
Thermal conductivity	110 W/ m · K
Electrical conductivity	17 m/Ω · mm <sup>2</sup>

RAL colour\* RAL 7037

GRANUM skygrey

RHEINZINK GmbH & Co. KG  
Bahnhofstraße 90  
45711 Datteln · Germany  
Tel.: +49 2363 605-490  
Fax: +49 2363 605-291  
E-Mail: info@rheinzink.com  
[www.rheinzink.com](http://www.rheinzink.com)

\* Color values are approximate values in the delivery condition, deviations in the surface treatment process are possible.